

kromoFlooring

Mühlbacher Straße 1 D-01561 Lampertswalde/Dresden Tel. +49 3522 33-30 ⋅ Fax +49 3522 33-399 www.mystyle-flooring.com ⋅

EDELHARZBÖDEN* - ELEGANT DESIGNER FLOORING My Dream - Technical Datasheet Direct Pressure Laminate, Level of use according to EN 13329: class 23/33 – AC6

* Composition of synthetic resin and natural wood







Heavy commercial use

30 year residential and 5 year commercial warranty**

ы	М	NS	ın	N
וט	IVI	чJ	ıv	ľ

dimension	thickness (d)	14 ± 0,50 mm · dmax - dmin ≤ 0,50 mm				
	length	1285 ± 0,50 mm				
	width (b)	192 ± 0,10 mm · bmax - bmin ≤ 0,20 mm				
profile	long side	twin clic	short side	1clic 2go pure		
groove	long side	real groove	short side	real groove		



				ar and a pair			
groove	long side	real groove	short side				
TOLERANCE							
squareness		EN 13329		≤ 0,20 mm			
straightness		EN 13329		≤ 0,30 mm			
flatness crosswise		EN 13329		concave: ≤ 0,15% · convex: ≤ 0,20%			
flatness length		EN 13329		concave: ≤ 0,50% · convex: ≤ 1,00%			
gaps between elements		EN 13329		average: ≤ 0,15 mm · max: ≤ 0,20 mm			
height difference between elements		EN 13329		average: ≤ 0,10 mm · max: ≤ 0,15 mm			
misalignment				± 2 mm			
TEST							
abrasion resistance		EN 13329		AC6 (≥ 8500 rpm)			
impact resistance		EN 13329		small ball ≥ 70 mm · big ball ≥1000 mm			
micro scratch resistance		EN 13329		≤ MSR-B2			
stain resistance	group 1 & 2	EN 13329		grade 5			
	group 3			≥ grade 4			
castor chair test		EN 13329		no change in appearance or damage, as defined per EN 425			
effect of a furniture leg		EN 13329		no damage shall be visible, when testet with foot type 0			
static indentation		EN 13329		≤ 0,05 mm			
light fastness		EN 13329		grey scale ≥ 4 at blue wool grade 6			
dimensional variations after changes in relative humidity		EN 13329		lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm			
locking strength		EN 13329		length ≥ 1 kN/m · width ≥ 2 kN/m			
surface soundness		EN 13329		≥ 1,25 N/mm²			
ENVIRONMENT							
emission of formaldehyde		EN 16516		class E1			
PHYSICAL BEHAVIOR							
fire behavior		EN 13501-1		Cfl s1			
slide resistance		EN 13893		technical class DS			
thermal resistance		EN 12667		0,108 (m ² K)/W ± 15%			
thermal conductivity		EN 12664		0,126 W/(m*K) ± 15%			
antistatic behavior		EN 1815		body voltage ≤ 2kV			

^{**}Detailed warranty conditions are available at www.mystyle-flooring.com

The data sheet is updated regularly to meet new technological standards. This version replaces all previous versions as well as those which are undated. This version takes effect upon creation. Version 02/2022